

2 Ton Epoxy

ORDERING INFORMATION

	<u>Stock No.</u> 14310 14260 20242	<u>Package Size</u> 28ml Dev-Tube 50ml Cartridge 400ml Cartridge
Description	A high strength, non-shrinking, adhesive/potting compound specially formulated for high clarity, good impact strength, and water resistance. The adhesive bond is resistant to weathering, solvents, and wide variations in temperature.	
Features	<ul style="list-style-type: none"> • Formulated for clarity • 100% reactive, no solvents • Good water and chemical resistance • Fills gaps and voids • Room temperature curing • Non corrosive 	
Recommended applications	<ul style="list-style-type: none"> • Bonding or potting electronic components and assemblies • Creating moisture-resistant seals • Fast-curing, thin set, bonding above 4°C • Suitable for bonding ceramics, ferrous and non-ferrous, ferrites, wood, glass and concrete 	

PRODUCT DATA

Physical Properties (Uncured)	Colour	Clear			
	Mixed Viscosity	5,000cps			
	Mixed Ratio by Volume and weight	1:1			
	Working time 28 grams @ 24°C	10 minutes			
	Functional cure @ 24°C	2 hours			
	Coverage 0.25mm thickness	15.18 cm ² /Kg			
	Specific volume	907 cm ³ /Kg			
	% solids by volume	100			
	Performance characteristics (cured)	7 days cured @ 24°C			
		Adhesive tensile shear, ASTM D1002	15.5 N/mm ²		
Operating temperature, dry		-40-93°C			
Cured density, ASTM D792		1.10 gm/cm ³			
Cured hardness, ASTM D2240		83D			
Dielectric strength, ASTM D149		600 volts/mil			
Compression strength, ASTM D695		75.86 N/mm ²			
Coefficient of thermal conductivity, ASTM D696		83			
7 days room temperature cure (30 days immersion)					
Chemical Resistance		Kerosene	Very good	Methanol	Fair
	Hydrochloric Acid	Fair	Toluene	Very good	
	Chlorinated Solvent	Very good	Ammonia	Very good	
	Sulphuric Acid 10%	Fair	Sodium Hydroxide 10%	Very good	

Please consult ITW Devcon for other chemicals

Epoxyes are very good in water, saturated salt solutions, leaded gasoline, mineral spirits, ASTM#3 oil and propylene glycol. Epoxyes are not recommended for long-term exposure to concentrated acids and organic solvents.

Unit 3, Shipton Way, Express Business Park, Northampton Road, Rushden, NN10 6GL, UK

ITW Devcon Industrial Products GmbH, Liebigstraße 21, 24145 KIEL, Deutschland/Germany



2 Ton Epoxy

APPLICATION INFORMATION

General Surface Preparation	2 Ton Epoxy works best on clean surfaces. If surface is oily or greasy, use Devcon Fast Cleaner 2000 Spray/Cleaner Blend 300 to degrease the surface. Surfaces should be free of heavy deposits of grease, oil, dirt or other contaminants or cleaned with industrial cleaning equipment such as vapor degreasers or hot aqueous baths. Abrading or roughing the surfaces of metals will increase the microscopic bond area significantly and optimize the bond strength.
Mixing	This product is available in cartridge and 28g Devtube form only. The cartridge should be used with the appropriate manual Applicator Gun and Static Mixer Nozzle. The Static Mixer Nozzle enables the epoxy to be dispensed, metered and directly applied to the surfaces to be bonded. Please note: Once the product cures in the nozzle it has to be thrown away and a new nozzle used. For small amounts use Devcon's 28g Devtube, which comes with its own plunger to extrude the two components at an equal rate.
Application	Apply mixed epoxy directly to one surface in an even film or as a bead. Assemble with the mating part within the recommended working time. Obtain firm contact between the parts to minimize any gap and ensure good contact of the epoxy with the mating part. A small fillet of epoxy should flow out the edges to show there is adequate gap filling. For very large gaps, apply epoxy to both surfaces and spread to cover the entire area, or make a bead pattern, which will allow flow throughout the joint. Let bonded assemblies stand for the recommended functional cure time before handling. They are capable of withstanding processing forces at this point, but should not be dropped, shock loaded or heavily loaded.
Cure	Full bond strength is reached in 16 hours.
Storage Shelf Life	Devcon Epoxy Adhesives should be stored in a cool dry place when not used for a long period of time. A shelf life of 3 years from date of manufacture can be expected when stored at room temperature (22°C) in their original containers
Precaution	For complete safety and handling information, please refer to the appropriate Material Safety Data Sheets prior to using this product.
Warranty	Devcon will replace any material found to be defective. Because the storage, handling and application of this material is beyond our control we can accept no liability for the results obtained.
Disclaimer	All information on this data sheet is based on laboratory testing and is not intended for design purposes. ITW Devcon makes no representations or warranties of any kind concerning this data. For product information visit www.devconeurope.com alternatively for technical assistance please call +44 (0) 870 458 7388 (UK) or +49 431 718830 (Germany)